


$T_p = 1400^\circ\text{C}$

5% G2 pyroxenite + 95% peridotite

Melt compositions at $P_{\text{final}} = 5$ kbar, no aging


Equilibrium melting

Peridotite




Pure disequilibrium melting

Peridotite




$Da = 0.1$


Peridotite



G2 Pyroxenite



G2 Pyroxenite



G2 Pyroxenite

